

Fuel Cell Testing Part II: EIS characterization

I – INTRODUCTION

To complete the characterization of the fuel cell carried out with common electrochemical techniques (scan or pulse of current or of potential) [1], Electrochemical Impedance Spectroscopy (EIS) investigations are intensively used and lead to additional information [2-4] such as:

- reactivity and structure of the interface,
- electrochemical reactions and mass transport limitation.

The aim of this note is to show the abilities of FC-Lab® and FCT series to perform EIS measurements and to analyze EIS data with Zfit (EIS modeling tool) included in EC-Lab® software.

II – SET-UP DESCRIPTION

FCT-150S with impedance and automatic water control was used and was monitored by FC-Lab®. FCT-150S was connected to fuel cell with the standard two-electrode connection (blue and white leads on the anode and the red lead on the cathode). The surface area of the fuel cell is 25 cm².

III – IMPEDANCE CHARACTERIZATION

Standard impedance techniques (potentio and galvano) are available in the FCT system controlled by FC-Lab®. In this note the macro techniques (several linked techniques) of FC-Lab® are highlighted, specially Staircase Galvanostatic Electrochemical Impedance Spectroscopy measurement (SGEIS).

SGEIS technique includes a scan of current with several GEIS experiments along the current scan. SGEIS settings are shown in Fig. 1.





Figure 1: SGEIS macro-technique window.

Figure 2 displays only the GEIS settings (more information on current scan settings are given in the previous note [1]). Settings are divided in two blocks. In the first one, the bias current is set. In our example, the box vs. init is ticked in order to perform EIS measurement at the current where the scan was stopped at the former loop. In the second block, frequencies scan (between F_i and F_f) and the intensity of the modulation (I_a) are defined. In our case, the scan is carried between 1 kHz and



100 mHz with an amplitude of 1 A.

Figure 2: GEIS technique parameters window.

Current scan is displayed in Fig. 3 and locations of the EIS measurements are indicated with red arrows.




Figure 3: Current scan during SGEIS macro technique. Red arrows show where GEIS experiments are performed.

The resulting data are displayed as Nyquist plot in Fig. 4.




Figure 4: Nyquist plots resulting of GEIS measurements. For clarity, only the loop # 0; 1; 2 and 7 are displayed.

The Nyquist plot can be plotted in 3D by ticking the 3D box 3D (Fig. 5). In this plot, the z-axis corresponds to the loop number.

IV – EIS DATA FITTING




Figure 5: 3D Nyquist plots.

FC-Lab® data (which are stored in “*.elt” format; EElectrochemical Text) have to be exported into EC-Lab® software in order to be fitted with Zfit. The export procedure is described in the first part of the next paragraph. Fit process and result analysis are discussed in the second part.

IV - 1 DATA IMPORTATION FROM FC-LAB® TO EC-LAB®

The import procedure is the following:

- in the “Experiment” menu, select “Import From Text” (Fig. 6),
- load the “*.elt” file of interest,
- in the block “Importation Parameters”, select FC-Lab® data in the “Text File format” combo box,
- in the “Importation” block, click on “Import” to create the “*.mpr” file,
- then, the resulting “*.mpr” file can be opened with EC-Lab®.

Note that it is also possible to import “*.log” file into EC-Lab®. This file contains gas pressure and temperature, potential of the cell,




Figure 6: Import From Text window.

IV - 2 ZFIT

As the Nyquist plots (Fig. 7) display two capacitive arcs at frequency of 20 and 0.5 Hz, the fit is performed with the following equivalent circuit $R_1+R_2/C_2+R_3/C_3$. Other equivalent circuits can be relevant for example $R+R/C+C/W_\delta$ as done in [3] with W_δ : Warburg element for convective diffusion.




Figure 7: The two capacitive arc at 20 and 0.5 Hz.

Table I displays the fitted resistance values. Further information about Zfit is available in EC-Lab® manual or in the application note #14 [5].

Table I: ZFit results.

Loop	$i/mA.cm^{-2}$	$R_1/m\Omega$	$R_2/m\Omega$	$R_3/m\Omega$
0	39	21.63	53.26	12.19
1	76	19.14	46.58	10.87
2	114	16.43	32.75	8.76
3	152	13.69	28.54	8.42
4	189	11.36	29.60	9.70
5	227	11.34	29.46	10.56
6	264	9.99	28.38	12.43
7	302	10.02	30.42	13.80

a. Contact resistance

The contact resistance, called R_1 , is due to the graphite plate, contact resistance, wires, ... Fig. 8 displays the change of this resistance versus the current density along the measurement. It is shown that R_1 decreases when current density increases. When fuel cell is working, water is produced. Then, this water production leads to an improvement of fuel

cell performance. This behavior was already reported in the literature [3].




Figure 8: R1 vs. current density.

b. Mass transfer

Diagram $R3/(R2+R3) = f(i)$ (Fig. 9) exhibits a constant slope beyond 50 mA.cm⁻². This behavior shows that the mass transfer contribution changes proportionally to the current [1].




Figure 9: R3/(R2+R3) vs. potential.

V – CONCLUSION

This note deals with EIS investigations on fuel cell. The first part describes the macro technique, named SGEIS. This protocol allows user to perform automatically successive EIS measurements along a current scan. The second part is focused on EIS data analysis. The compatibility between FC-Lab® and EC-Lab® software makes the EIS analysis easy. This allows user to determine some characteristic parameters of the fuel cell, for example contact resistance, mass transfer, ...

Data files can be found in :

C:\Users\xxx\Documents\EC-Lab\Data\Samples\Battery\AN31-32_Manip

REFERENCES

- 1) [Application Note #31](#) “Fuel Cell Testing, Part I: Overview and I/E characterizations”
- 2) E. Barsoukov, J.R. Macdonald, *Impedance spectroscopy. Theory, Experiment, and Applications.*, Wiley, Hoboken, USA (2005).
- 3) J.-M Le Canut, R. Latham, W. Mérida, D.A. Harrington, *J. of Power Sources*, 192 (2009) 457.
- 4) J.-P Diard, B. Le Gorrec, C. Montella, C. Poinignon, G. Vitter, *J. of Power Sources*, 74 (1998) 244.
- 5) [Application Note #14](#) “ZFit and equivalent electrical circuits”

Revised in 07/2018